



Promising Adsorption of Sulfidic Acid Gases Using Wet Banana Plant Adsorbent (*Musa* spp.)

Haryono S. Huboyo*, Badrus Zaman, Bimastyaji S Ramadan &
Anastasia D Prinaningrum

Environmental Engineering Department, Faculty of Engineering,
Diponegoro University, Jalan Prof. H. Soedarto, SH Tembalang Semarang 50275
Indonesia

*E-mail: haryono.setiyo.huboyo@ft.undip.ac.id

Highlights:

- Banana plant waste can be used as gas adsorbent.
- The leaves of the banana plant are the most effective in removing pollutants.
- Removal of gaseous pollutants occurs in less than 15 minutes.

Abstract. Bananas have the highest production rate among fruits in Indonesia, which leads to the generation of a significant amount of banana fruit solid waste. In this study, we assessed the potential use of banana waste to remove hydrogen sulfide (H_2S) gas. In particular, the purpose of this study was to analyze the efficiency of banana waste as an adsorbent for H_2S gas. We tested the stems, leaves, and peels of banana plants as H_2S gas adsorbents with varying contact times. To obtain a microscopic view of the adsorbents before and after the experiment, we conducted measurements using scanning electron microscopy with dispersive X-ray spectroscopy. The banana leaves, stems, and peels were found to have H_2S gas absorption efficiency values of 76.52%, 51.83%, and 6.44%, respectively. Based on the experiment, the leaves of the banana plant appear to be the best adsorbents, with an adsorption capacity of 1.67 mg/g. The results also revealed that there was a change in the fiber and stomata appearance of the banana leaves after the adsorption process. Overall, this research indicates that banana leaves have the potential to be used as effective H_2S adsorbents.

Keywords: *adsorption; air pollution; gas; odor; plant.*

1 Introduction

In 2018, bananas were ranked as the largest contributor to fruit production in Indonesia, with a total production figure of 7.26 million tons, which is above the production figures for mangoes, oranges, pineapples, and durian [1]. Banana production has since increased by 1.42% (101,698 tons) and still ranks first among the fruit production contributors. East Java is the largest banana-producing province, with a total production of 2.06 million tons annually,

accounting for 28.36% of the total national banana production. However, the export of bananas is not as high as that of other fruits, such as salak, mangoes, and mangosteen. The high banana fruit production leads to high production of waste, including skins (peels) and stems. Many researchers have experimented with waste from banana plants, for example, as innovative food ingredient, alternative energy resource, or an essential material in water and waste treatment. Researchers have also used banana peels as antidepressant candy [2] or as an ingredient for milk drinks [3]. The banana plant can also be used as an environmentally friendly alternative for long-lasting battery cells [4], as a raw material for producing bioethanol, or as a complementary material to increase biogas production [5].

Hydrogen sulfide (H_2S) can have adverse effects on human health, especially if one is exposed to H_2S through the air. The lungs quickly absorb the gas [6], meaning the respiratory system is the body system that is most sensitive to H_2S exposure [7]. H_2S at a concentration of 500 ppm can cause pulmonary edema and even death. It is included in the asphyxiant group because its main effect is to paralyze the respiratory center, meaning death can be caused due to a stoppage in breathing.

Adsorption methods can be widely applied to recover specific air quality from air pollutants if highly selective adsorbents are used. Further, the use of low-cost, sustainable, selective, and eco-friendly adsorbents could be an effective advanced technique to recover air quality. Contemporary researchers are showing great interest in developing new adsorbent materials with excellent properties, diverse compositions, and high selectivity. Our literature survey showed that over the past few decades, a variety of low-cost alternative adsorbents have been proposed, including coconut shells [8], Acacia mangium wood [9], rice husk [10], pomegranate shell [11], bamboo [12], banana waste [13], oil palm waste [12], and date stones [14]. A banana plant can produce fruit once in its lifetime, meaning after fruit harvesting the whole plant is discarded as waste. If this huge amount of waste can be transformed into useful material, it would be of great help to banana growers/farmers. Otherwise, dumping this waste into water or leaving it under humid conditions leads to methane and carbon monoxide gas formation, while burning it can produce large quantities of carbon dioxide gas.

Many studies have been conducted on the use of banana plants (*Musa* spp.) as bio-adsorbents, which were found to be mainly applicable to liquid waste. Banana peels can be used for the removal of heavy metals from wastewater, as demonstrated by Anwar [15], Vilardi [16], Nada [17], Ali [18], and Ali Ashraf [19]. Bananas are also effective at removing organic substances (especially dyes) from wastewater, as shown by Stavrinou [20], Danish [13], and Munagapati [21]. Furthermore, the use of bananas as adsorbents of waste gas was demonstrated by

Promising Adsorption of Sulfidic Acid Gases Using Wet Banana Plant Adsorbent (*Musa* spp.)

Shen [22] for volatile benzene and toluene. In Indonesia, several studies have revealed the role banana peels can play in removing polluting gases, such as those from motorized vehicles [23]. Sumiyati [24] have listed potential uses of banana plants for removing gaseous pollutants, including sulfidic acid gas. However, no research has been conducted yet to assess banana plants as bio-adsorbents to remove odors from polluting gases, such as H_2S . This study aimed to investigate the feasibility of using banana plants (without conversion into activated carbon) as an adsorbent of H_2S gases. The research was conducted in two stages: assessing the adsorbent type (fresh leaves, stems, and banana peels) in removing H_2S and examining the best adsorbent to remove H_2S . The results are expected to be applicable on a larger scale, for example for eliminating odors in the waste industry, determining buffer zones in landfills (as many buffer zones in Indonesia's landfills are covered with banana plants), possibly removing the smells of livestock and agriculture, and purifying biogas from H_2S contaminants.

2 Materials and Method

2.1 Materials Preparation

The banana plant components used in this study are depicted in Figure 1. Fresh banana leaves, banana fruit, and banana stems were cleaned with a damp cloth and allowed to dry for approximately 15 minutes. Then, they were cut with the following details: the banana leaves were chopped to a size of 10 mm x 1 mm, the banana stems were chopped to a size of 2 mm x 2 mm, and the banana peels were chopped to a size of 2 mm x 2 mm. After being chopped, the adsorbent was weighed and put into an adsorbent tube until full. Based on this criterion, the adsorbent mass we got from the banana leaves, banana stems, banana peel was 15 g, 27 g, 32 g respectively. The difference in mass of the adsorbent used was influenced by the density of each adsorbent.




Figure 1 Materials from banana components used in this study.

2.2 H₂S Gas Preparation and Measurement

A schematic diagram of the experimental setup is shown in Figure 2. In this experiment, we used a standard Erlenmeyer flask (Pyrex) as well as a plug, tubing, air sampler/impinger (AGS), analytical balance (Mettler Toledo ME 204), and UV–Vis spectrophotometer (Thermoscientific Genesys 10S). The procedure for creating the H₂S gas used here was modified from Prasetyo [25]. First, 0.18 g of FeS (Pudak Sci) and 4.5 mL of 1-M HCl (Merck) were reacted. The gas formed was then left to stand for 1 h to ensure a complete reaction and was then transferred from the air sampler/impinger to an adsorbent tube and finally to the adsorbent solution ZnSO₄ (Merck). H₂S gas withdrawal was carried out with a constant flow rate of 0.5 L/m for five variations of contact time (15, 17, 20, 22, and 25 min). In this experiment, measurements were conducted under room temperature, i.e., 25 °C.




Figure 2 Experimental setup for H₂S adsorption.

The general mechanism of H₂S gas removal has been reviewed elsewhere [26]. For the measurement of H₂S levels via the methylene blue method using a spectrophotometer we referred to Indonesian National Standard (SNI) 19-7117.7-2005 [27]. A solution containing 50 mL of the measurement sample was removed from the device experiment chain and rinsed using distilled water. The sample was then diluted to 100 mL with distilled water. Additionally, 50 mL of absorbent solution was prepared and then diluted with distilled water to a volume of 100 mL (blank).

A 20-mL sample solution was piped into a measurement tube. 2 mL of para-amino dimethyl aniline and 1 mL of FeCl₃ were added to each tube, and the samples were homogenized. Next, each tube was diluted with distilled water to a volume of 25 mL, homogenized again, and left to stand for 30 min. The absorbance of the measurement sample solution was measured at a wavelength of 670 nm, and the concentration of H₂S gas was calculated using a calibration curve.

Promising Adsorption of Sulfidic Acid Gases Using Wet Banana Plant Adsorbent (*Musa spp.*)

2.3 Calibration Curve and Adsorption Capacity

The adsorption capacity is defined as the amount of H₂S absorbed per unit weight of the adsorbent. The Freundlich and Langmuir adsorption isotherms (mg/g) were used as models. The Freundlich equation is as follows:

$$\log q = \log K + 1/n \log C.$$

where: q = concentration of adsorbed adsorbate, C = concentration of adsorbate at equilibrium (mg/L), K = equilibrium constant, N = empirical constant depending on the nature of the substance.

The Langmuir equation is as follows:

$$1/q = 1/(q_m K C) + 1/q_m.$$

In these equations, q = concentration of adsorbed adsorbate, q_m = maximum capacity of adsorbent (mg), K = equilibrium constant, C = concentration of adsorbate at equilibrium (mg/L).

Based on the above equations, a linear adsorption isotherm curve was generated, from which the values of the regression coefficient, slope, intercept, and adsorption capacity could later be drawn. The solution concentration of absorbed H₂S was then measured using the methylene blue method with a UV-Vis spectrophotometer. We then used a calibration curve, which had been made in advance, to determine the absorbed H₂S concentration.

The calibration curve consisted of five variations of the H₂S working solution (0, 5, 10, 15, and 20 mL). The absorbance and concentration results were plotted on a graph to obtain a linear equation in the form of $y = ax + b$. This equation was then used to calculate the amount of measured H₂S. The results of the calibration curve are shown in Figure 3. The linear equation obtained was $y = 0.375x + 0.076$, with a slope of 0.375 and an intercept of 0.076.




Figure 3 Linear equation of the H₂S calibration curve.

3 Result and Discussion

3.1 Measurement Results of H₂S Gas Concentration

The research was carried out in triplicate to obtain a better estimated concentration value. Table 1 shows the concentration of H₂S (mg/L) with variation of adsorbent type and contact time.

In this study, the concentrations were normalized with control treatment (no adsorbent). We assumed there would be no adsorption in the control treatment, except negligible gas adsorption in the adsorption device (tubing, adsorbent tube).

Table 1 Average H₂S Concentration (mg/L) after contact with an adsorbent.

Adsorbent Type	Contact Time (min)				
	15	17	20	22	25
Leaf	1.951±0.513	2.344±0.030	7.304±0.193	8.384±0.135	9.131 ±0.106
Stem	4.003±0.042	6.644±0.219	7.588±0.028	8.680±0.125	9.501 ±0.200
Peel	8.236±0.308	8.374±0.277	9.060±0.124	9.357±0.063	10.157±0.104
No adsorbent	8.309±0.147	8.847±0.061	9.419±0.086	9.938±0.180	10.780±0.112

It was found that the concentration of H₂S without adsorbent increased with contact time, with the lowest concentration being 8.3 mg/L and the highest concentration 10.78 mg/L. The difference in concentration among the five contact times was quite significant (one-way ANOVA at $p < 0.05$), as the contact time interval given was relatively short (around 2 to 3 min). Several different physical characteristics were noted when measurements were made with and without the adsorbents. At the time of measurement, there was a change in the adsorbent solution's color; the longer the contact time, the cloudier the adsorbent solution became. During the measurement without adsorbent, an odorless white fog appeared, while when an adsorbent was used no fog appeared. The zinc sulfide compound caused a change in color and moisture. These results came from the reaction between H₂S and the adsorbent solution (ZnSO₄). According to Moreira [28], the longer the contact time, the greater the adsorbent solution's ability to absorb the adsorbate. This is due to the long contact time between the adsorbent and the adsorbate, allowing additional bonds to form until the equilibrium point is reached. However, when the contact time between the adsorbent and the adsorbate is too long, the adsorbent saturates and the adsorbate is released.

3.2 Bananas Adsorbent Characteristics

Observation of the adsorbent's characteristics before and after the measurements was carried out to support the research results. Before the measurements, the banana leaves were bright green and looked fresh. After the measurements were

Promising Adsorption of Sulfidic Acid Gases Using Wet Banana Plant Adsorbent (*Musa spp.*)

made, the most noticeable difference was in the leaves, which appeared paler and some of the pieces had turned brown (Figure 4).



(a)



(b)

Figure 4 Banana adsorbents before (a) and after (b) the adsorption process.

Figure 5 shows the differences in the banana leaf adsorbent with and without H_2S . Before contact with H_2S , many leaf fibers can be seen crossing the leaf epidermal cells and the stomata are still visible. After the H_2S had passed through them, the leaf fibers were no longer visible. Thickened leaf epidermal cells could be seen, so that their striations became visible. The stomata were damaged, as marked by the presence of elements attached to them. From the scanning electron microscopy (SEM) observation results it can be concluded that the H_2S that had passed through the banana leaf adsorbent caused it to deteriorate.

Several other studies based on SEM analysis about the role of stomata in capturing air pollutants have proved this. For example, 500x magnification SEM showed that fine particles smaller than $0.1\ \mu\text{m}$ were able to penetrate leaf tissue through stomata [29]. Song, *et al.* [30] found the fine particles for up to $2\ \mu\text{m}$ (1000x magnification SEM). In addition, Zha, *et al.* [31], using 1000x magnification SEM, found that capturing air contaminants, i.e. particles and PAH, could be facilitated by grooves surrounding the stomata.




Figure 5 Changes of fiber (a)(b) and stomata (c)(d) before and after adsorption.

3.3 Overall Adsorption Isotherm

Based on the calculation results obtained using the Freundlich and Langmuir isotherms (Table 2), it was found that the banana leaves had a consistently large adsorption capacity, whereas the banana peels had a small capacity. In particular, the banana leaf adsorption capacity reached 16 to 22 times that of the banana peels. However, differences could be seen among the results of the different adsorbent types when using the two isotherm models. When the Freundlich isotherm was used, the results regarding the adsorption of leaves and stems were almost the same, but when the Langmuir isotherm was used, the values of the adsorption of leaves were more than twice those of the banana stems. Based on

Promising Adsorption of Sulfidic Acid Gases Using Wet Banana Plant Adsorbent (*Musa spp.*)

these results it can be concluded that banana leaves have the greatest potential for use as H₂S adsorbents.

Table 2 Average H₂S concentration (mg/L) after contact with an adsorbent.

Adsorbent Type	Freundlich Isotherm		Langmuir Isotherm	
	R	Capacity (mg/g)	R	Capacity (mg/g)
Leaf	0.94	1.6750	0.90	1.4310
Stem	0.92	1.6761	0.87	0.6384
Peel	0.58	0.1063	0.42	0.0635

According to Viena [23], banana plants are usually used as adsorbents to reduce pollutant gases and can reach an adsorption capacity of up to 952 mg/g. However, in such a case, the bananas are usually prepared in the form of activated carbon. The analysis results of the efficiency of each obtained adsorbent are shown in Figure 6.




Figure 6 Removal efficiency for H₂S adsorption.

The banana leaf adsorbent had the highest efficiency at a contact time of 15 min, with a value of 76.52%. However, as the contact time increased, the absorption efficiency of the H₂S gas concentration decreased slowly.

The efficiency value decreased quite drastically for a contact time of 20 min, from 73.51% to 22.45%, and finally, the lowest efficiency was reached at a contact time of 25 min (15.30%). The highest absorption efficiency of H₂S in the banana stem adsorbent reached 51.83% at a contact time of 15 min, while the lowest

efficiency of 11.87% was observed at a contact time of 25 min. The least significant decrease in efficiency occurred between contact times of 15 and 17 min, with a difference of 26.93%. This result indicates that the saturation time of the banana stem adsorbent in absorbing gas was 15 min and that when the contact time for H₂S absorption increased past this point, the efficiency decreased. The efficiency level of the absorption of H₂S gas for the banana peel adsorbent fluctuated significantly. The highest efficiency of 6.44% was observed at a contact time of 25 min, while the lowest efficiency of 0.89% was observed at a contact time of 15 min. The fluctuations in the data were caused by the unstable condition of the adsorbent. One of the factors in this is the wet nature of the banana skin, which also has mucus on its surface.

The H₂S absorption efficiency values from the three adsorbents contrasted significantly with one another. The banana peels had a relatively small and fluctuating efficiency of H₂S absorption (<6%). From the fluctuating efficiency results it can be concluded that banana peels are not an optimum adsorbent media. Banana stems had their highest H₂S absorption efficiency (51.8%) at 15 min of contact time and their lowest efficiency (11.87%) at 25 min of contact time. The banana stems thus showed a significant decrease in absorption efficiency when compared with the banana peels. According to Rodriguez [32], banana stems have fiber consisting of 60% to 65% cellulose, 6% to 8% hemicellulose, 5% to 10% lignin, and 10% to 15% water. Hemicellulose is highly useful and can be applied as an adsorbent to remove oil, heavy metals, and pollutants [33].

The adsorption efficiency is also influenced by the length of contact time in the adsorption process. Based on the research results it can be seen that the best adsorption efficiency was obtained at 15 min. This is because the adsorption process reached an optimum state at this time. After 15 min of contact time, the adsorption efficiency decreased due to the lengthy contact time between the adsorbent and the adsorbate, which caused the adsorbent to saturate and the adsorbate to be released. At the same time, the adsorbent works inefficiently before the optimum conditions are reached. Based on the three adsorbent types and the five contact times used in this study it can be concluded that banana leaves are the best adsorbents and have an optimum contact time of 15 min. The fiber in banana leaves has a higher density than that in banana stems and peels. Moreover, banana leaves have more stomata when compared to branches and peels. Stomata are an important pathway for air pollutant uptake in plants [34]. Thus, having more stomata means having greater potential to absorb gaseous pollutants. The ability of stomata to absorb gas was also investigated in Wei, *et al.* [35], where sulfuric acid gas could be captured molecularly by the stomata in addition to being captured in the stem and bark. This was confirmed by Tiessen [36], who found that stomata facilitate the exchange of gaseous pollutants. This also explains why pollutants are found in the stomata [37]. The rate of gas exchange

Promising Adsorption of Sulfidic Acid Gases Using Wet Banana Plant Adsorbent (*Musa spp.*)

permeability depends on the degree of stomatal opening at 4 to 10 nm [38]. Due to the deposition of pollutants in the stomata, there is a reduction in the average stomata pore area [39].

The absorption capacity increases as the surface area of the absorbent increases. For example, Hoang, *et al.* [40] revealed that the uptake of air pollutants in polyurethane rice straw was about 3 to 4 times higher than that of artificial pure polyurethane due to the higher surface area. Huang, *et al.* [41] found that molecularly imprinted polymers (MIPs), which have a higher surface area than other adsorbents, gave the best results in capturing gaseous pollutants. Various banana plants in Indonesia have a higher number of stomata on the abaxial surface. Auliya, *et al.* [42] reported that some banana plant leaves can have 21-42 stomata/field of view based on SEM analysis.

Based on the results of electron-dispersive X-ray spectroscopy (EDX) without H₂S (shown in Table 3 and Figure 7), the fresh banana leaves were found to possess several constituent elements, including C, O, N, K, Mg, Cl, and Si. In fresh banana leaves, the lowest weight percentage value belonged to Si, which had a percentage atomic weight of 0.07, and the highest percentage value belonged to C, which had a percentage atomic weight of 65.47. In the results of EDX with H₂S, all the same elements were found. However, there was also an additional element, S, which has a percentage atomic weight of 0.24. The presence of S confirms that H₂S was adsorbed into the banana leaves. Further research is needed to analyze contact times under 15 min. In future work, adsorbent cutting should also be homogenized so that the adsorption capacity is evenly distributed.

Table 3 Average H₂S concentration (mg/L) after contact with an adsorbent.

Element	Without H ₂ S	With H ₂ S
	% Atomic weight	% Atomic weight
C	65.47	67.68
O	28.53	17.54
N	4.64	5.92
K	0.71	3.66
Mg	0.42	0.14
Cl	0.16	4.75
Si	0.07	0.21
S	—	0.24




Figure 7 EDX graph results before and after H₂S adsorption.

4 Conclusion

Based on the experiment in this study, three banana components, i.e. leaves, stems, and banana peels, had H₂S gas absorption efficiency values of 76.52%, 51.83%, and 6.44%, respectively. Banana leaves having the highest absorption efficiency may be caused by the presence of stomata in the leaves, which is supported by changes in the appearance of fibers and stomata in banana leaves after the adsorption process. This study showed that banana leaves have good potential to be used as adsorbent of H₂S gas.

Acknowledgement

This work was funded by *Direktorat Riset dan Pengabdian Masyarakat, Kementerian Riset dan Teknologi/Badan Riset dan Inovasi Nasional Republik Indonesia* No. 225-101/UN7.6.1/PP/2020.

Promising Adsorption of Sulfidic Acid Gases Using Wet Banana
Plant Adsorbent (*Musa* spp.)

References

- [1] Central Bureau of Statistics, *Statistics of Indonesia's Annual Fruit and Vegetable Crops*, 2018.
- [2] Gurumalles, P., Ramakrishnan, B. & Dhurai, B., *A Novel Metalloprotease from Banana Peel and Its Biochemical Characterization*, Int. J. Biol. Macromol., **134**, pp. 527-535, 2019.
- [3] Batista, A.L.D., *Developing A Synbiotic Fermented Milk Using Probiotic Bacteria and Organic Green Banana Flour*, J. Funct. Foods, **38**, pp. 242-250, 2017.
- [4] Huang, S.R., Chung, C.H., Leu, H.J., Sim, C.Y.D. & Lin, C.Y., *The Living Banana Plant as A Long-Lasting Battery Cell*, Int. J. Green Energy, **13**(7), pp. 650-654, 2016.
- [5] Guerrero, A.B., Ballesteros, I. & Ballesteros, M., *The Potential of Agricultural Banana Waste for Bioethanol Production*, Fuel, **213**, pp. 176-185, 2018.
- [6] Collins, J. & Lewis, D., *Hydrogen Sulfide: Evaluation of Current California Air Quality Standards with Respect to Protection of Children*, Air Toxicol. Epidemiol. Sect. Calif. Off. Environ. Heal. Hazard Assess., 2000.
- [7] US EPA, Hydrogen Sulfide 7783-06-4, Integr. Risk Inf. Syst. Toxic. Summ. Hydrog. Sulfide, pp. 1-17, 2003. DOI: 10.1002/0471701343.sdp13953.pub2.
- [8] Dwivedi, C.P., Sahu, J.N., Mohanty, C.R., Mohan, B.R. & Meikap, B.C., *Column Performance of Granular Activated Carbon Packed Bed for Pb (II) Removal*, J. Hazard. Mater., **156**(1-3), pp. 596-603, 2008.
- [9] Danish, M., Hashim, R., Ibrahim, M. N. M. M., Rafatullah, M., Ahmad, T. & Sulaiman, O., *Characterization of Acacia Mangium Wood Based Activated Carbons Prepared in the Presence of Basic Activating Agents*, BioResources, **6**(3), pp. 3019-3033, 2011.
- [10] Sahu, J.N., Agarwal, S., Meikap, B.C. & Biswas, M.N., *Performance of A Modified Multi-Stage Bubble Column Reactor for Lead (II) and Biological Oxygen Demand Removal from Wastewater Using Activated Rice Husk*, J. Hazard. Mater., **161**(1), pp. 317-324, 2009.
- [11] Ghaedi, M., Tavallali, H., Sharifi, M., Kokhdan, S.N. & Asghari, A., *Preparation of Low Cost Activated Carbon from Myrtus Communis and Pomegranate and Their Efficient Application for Removal of Congo Red from Aqueous Solution*, Spectrochim. Acta Part A Mol. Biomol. Spectrosc., **86**, pp. 107-114, 2012.
- [12] Rafatullah, M., Ahmad, T., Ghazali, A., Sulaiman, O., Danish, M. & Hashim, R., *Oil Palm Biomass as A Precursor of Activated Carbons: A Review*, Crit. Rev. Environ. Sci. Technol., **43**(11), pp. 1117-1161, 2013.

- [13] Ahmad, T. & Danish, M., *Prospects of Banana Waste Utilization in Wastewater Treatment: A Review*, J. Environ. Manage., **206**, pp. 330-348, 2018.
- [14] Danish, M., Hashim, R., Ibrahim, M.N.M. & Sulaiman, O., *Optimized Preparation for Large Surface Area Activated Carbon from Date (Phoenix Dactylifera L.) Stone Biomass*, Biomass and Bioenergy, **61**, pp. 167-178, 2014.
- [15] Anwar, J., Shafique, U., Salman, M., Dar, A. & Anwar, S., *Removal of Pb (II) and Cd (II) from Water by Adsorption on Peels of Banana*, Bioresour. Technol., **101**(6), pp. 1752-1755, 2010.
- [16] Vilardi, G., Di Palma, L. & Verdone, N., *Heavy Metals Adsorption by Banana Peels Micro-Powder: Equilibrium Modeling by Non-Linear Models*, Chinese J. Chem. Eng., **26**(3), pp. 455-464, 2018.
- [17] Nada, A.M.A., El-Gendy, A.A. & Mohamed, S.H., *Banana Leaves as Adsorbents for Removal of Metal Ions from Waste Water*, Carbohydr. Polym., **82**(4), pp. 1025-1030, 2010.
- [18] Ali, A., Saeed, K. & Mabood, F., *Removal of Chromium (VI) from Aqueous Medium Using Chemically Modified Banana Peels as Efficient Low-Cost Adsorbent*, Alexandria Eng. J., **55**(3), pp. 2933–2942, 2016.
- [19] Ali, A., *Removal of Mn (II) from Water Using Chemically Modified Banana Peels as Efficient Adsorbent*, Environ. Nanotechnology, Monit. Manag., **7**, pp. 57-63, 2017.
- [20] Stavrinou, A., Aggelopoulos, C.A. & Tsakiroglou, C.D., *Exploring the Adsorption Mechanisms of Cationic and Anionic Dyes onto Agricultural Waste Peels of Banana, Cucumber and Potato: Adsorption Kinetics and Equilibrium Isotherms as a Tool*, J. Environ. Chem. Eng., **6**(6), pp. 6958-6970, 2018.
- [21] Munagapati, V.S., Yarramuthi, V., Kim, Y., Lee, K.M. & Kim, D.S., *Removal of Anionic Dyes (Reactive Black 5 and Congo Red) from Aqueous Solutions Using Banana Peel Powder as an Adsorbent*, Ecotoxicol. Environ. Saf., **148**, pp. 601-607, 2018.
- [22] Shen, X., *Record-High Capture of Volatile Benzene and Toluene Enabled by Activator Implant-Optimized Banana Peel-Derived Engineering Carbonaceous Adsorbents*, Environ. Int., **143**, 105774, 2020.
- [23] Viena, V. & Wardani, S., *Application of Banana Peels Waste as Adsorbents for The Removal of CO₂, NO, NO_x, and SO₂ Gases from Motorcycle Emissions*, in Materials Science and Engineering Conference Series, **334**(1), 12037, 2018.
- [24] Sumiyati, S., Huboyo, H.S. & Ramadan, B.S., *Potential Use of Banana Plant (Musa spp.) as Bio-sorbent Materials for Controlling Gaseous Pollutants*, in E3S Web of Conferences, **125**, 3015, 2019.

Promising Adsorption of Sulfidic Acid Gases Using Wet Banana
Plant Adsorbent (*Musa* spp.)

- [25] Prasetyo, H.B., *Development of Hydrogen Sulfide Gas Sensor Based on Lead Acetate Dry Reagent*, Undergraduate Thesis, Faculty of Mathematics and Natural Sciences, Jember University, Jember, Indonesia, 2002.
- [26] Mandasari, W., Sitorus, B. & Jati, D.R., *Manufacturing and Characterizing the H₂S Gas Adsorbent from Natural Zeolite*, J. Kim. Khatulistiwa, **3**(2), pp. 112-119, 2014. (Text in Indonesian)
- [27] Indonesian National Standard (SNI), *Exhaust Emissions – Non Mobile Sources – Section 7: Test Method for Hydrogen Sulfide (H₂S) Level by the Methylene Blue Method Using Spectrophotometer*, SNI-19-7117.7-2005. (Text in Indonesian)
- [28] Moreira, R., Peruch, M.G. & Kuhn, N.C., *Adsorption of Textile Dyes on Alumina. Equilibrium Studies and Contact Time Effects*, Brazilian J. Chem. Eng., **15**(1), pp. 21-28, 1998. DOI: 10.1590/S0104-66321998000100002.
- [29] Ottel , M., van Bohemen, H.D. & Fraaij, A.L., *Quantifying the Deposition of Particulate Matter on Climber Vegetation on Living Walls*, Ecol. Eng., **36**, pp.154-162, 2010.
- [30] Song, Y., Maher, B.A., Li, F., Wang, X., Sun, X., Zhang, H., *Particulate Matter Deposited on Leaf of Five Evergreen Species in Beijing, China: Source Identification and Size Distribution*, Atmos. Environ., **105**, pp. 53-60, 2015.
- [31] Zha, Y., Liu, X., Tang, J. & Zhang, Y., *PAHs in Foliage Dust of Typical Tree Species with Urbanization Gradient in Nanjing, China*, Pol. J. Environ. Stud., **27**(3), pp. 1359-1370, 2018.
- [32] Rodr guez, L.J., Cardona, C.A. & Orrego, C.E., *Water Uptake, Chemical Characterization, and Tensile Behavior of Modified Banana–Plantain Fiber and Their Polyester Composites*, Polym. Compos., **37**(10), pp. 2960-2973, 2016.
- [33] Kudaligama, K., Thurul, W.M. & Yapa, P.A.J., *Effect of Bio-Brush Medium. a Coir Fibre Based Biomass Retainer on Treatment Efficiency of an Anaerobic Filter Type Reactor*, Journal of the Rubber Research Institute of Sri Lanka, **87**, pp. 15-22, 2005.
- [34] Treesubsuntorn, C. & Thiravetyan, P., *Removal of Benzene from Indoor Air by Dracaena Sanderiana: Effect of Wax and Stomata*, Atmos. Environ., **57**, pp. 317-321, 2012.
- [35] Wei, X., Lyu, S., Yu, Y., Wang, Z., Liu, H., Pan, D., Chen, J., *Phylloremediation of Air Pollutants: Exploiting the Potential of Plant Leaves and Leaf-associated Microbes*, Front. Plant Sci., **8**, pp. 1-23. 2017.
- [36] A. Tiessen, A., *The Fluorescent Blue Glow of Banana Fruits is Not Due to Symplasmic Plastidial Catabolism but Arises from Insoluble Phenols Esterified to the Cell Wall*, Plant Sci., **275**, pp. 75-83. 2018.
- [37] Hamidah, D. Putri, H. Purnobasuki, *Correlation of Lead (Pb) Content Towards the Number of Stomata on the Plant Dracaena Marginata*

- Tricolor in Some Places of Surabaya City*, E3S Web Conf., **153**, pp. 1-7, 2020.
- [38] Kvesitadze, E., Sadunishvili, T. & Kvesitadze, G., *Mechanisms of Organic Contaminants Uptake and Degradation in Plants*, World Academy of Science, Engineering and Technology. World Academy. Scien. Engi. Technol., **55**, pp. 458-468, 2009.
 - [39] Grantz, D.A., Karr, M. & Burkhardt, J., *Heterogeneity of Stomatal Pore Area Is Suppressed by Ambient Aerosol in the Homobaric Species, Vicia faba*, Front. Plant Sci., **11**, 897, 2020.
 - [40] Hoang, A.T., Le, V.V., Al-Tawaha, A.R.M.S., Nguyen, D.N., Noor, M.M. & Pham, V.V., *An Absorption Capacity Investigation of New Absorbent Based on Polyurethane Foams and Rice Straw for Oil Spill Cleanup*, Pet. Sci. Technol., **36**, pp. 361-370. 2018.
 - [41] Huang, Y., Su, W., Wang, R. & Zhao, T., *Removal of Typical Industrial Gaseous Pollutants: from Carbon, Zeolite, and Metal-Organic Frameworks to Molecularly Imprinted Adsorbents*, Aerosol Air Qual. Res., **19**, pp. 2130-2150. 2019.
 - [42] Auliya, I., Hapsari, L. & Azrianingsih, R., *Comparative Study of Leaf Stomata Profiles Among Different Ploidy Levels and Genomic Groups of Bananas (Musa L.)*, IOP Conf. Ser.: Earth Environ. Sci., **391**, 012037, 2019.